

## PRODUCT DATA

Date: June 2009

Code: 01529/30

# IDENDEN SPRAYABLE VAPOUR BARRIER COATING ET-150 AF

Idenden Sprayable Vapour Barrier Coating ET-150 AF is ideal for applications in the thermal insulation industry as a vapour barrier coating for internal and external insulated piping, equipment and air conditioning ducting. It is also suitable as an asbestos encapsulant. Idenden Sprayable Vapour Barrier Coating ET-150 AF is a white coloured, high quality polymer emulsion. It is easily applied by spray or brush to provide a durable and flexible, water-resistant finish over a wide service temperature range. Idenden Sprayable Vapour Barrier Coating ET-150 AF has Class 0 compliance and therefore dries to form a flame resistant finish.

### Features

- Easily applied by spray or brush
- Dries to form a flexible, durable and water-resistant finish
- Solvent free
- Class 0 compliance
- Anti-Fungal Properties

### Product Characteristics

Colour	White
Form	Thixotropic liquid
Weight per litre	1.26 kg 60% solids
Composition	Co-polymer emulsion
Packaging	19 litre drums
Shelf life/storage	At least 12 months from date of manufacture when stored unopened in a cool, dry place within the temperature range +5°C to +25°C and out of direct sunlight. PROTECT FROM FROST

### Typical Performance Data (approx.)

Drying time	<i>Touch:</i> 2 hours <i>Through:</i> 24 hours
Service temperature	-29°C to +82°C
Application temperature	Above +5°C (external work should not be completed in poor drying conditions or when rain is imminent)
Reaction to fire	<i>Wet:</i> Non-flammable <i>Dry:</i> Independently tested to BS 476 Part 6 – Pass Part 7 – Class 1 Building regulations – Class 0
Coverage	0.5 – 4.0 square metres per litre per coat (depending on substrate and performance requirements)

Water Vapour Permeance (0.034 g/sMN) (0.6 perms) at 1 mm dry film thickness (ASTM E96 Method A)

LEED IEQ 4.2 Idenden Sprayable Vapour Barrier Coating ET-150 AF meets the requirements for LEED IEQ 4.2 Low Emitting Materials, Adhesives and Sealants

Solvent for cleaning up *Wet:* Water  
*Dry:* White spirit

### Directions for use

#### IMPORTANT

Before embarking on any work involving Idenden Sprayable Vapour Barrier Coating ET-150 AF, the separate Safety Data Sheet should be carefully studied by those carrying out the work.

1. Surfaces should be clean, dry and free from dust, oil, grease and any loose materials.
2. A) PIPE OR DUCT INSULATION  
Using spray or brush, apply Idenden Sprayable Vapour Barrier Coating ET-150 AF to the entire surface. Embed a reinforcement membrane such as scrim canvas or glass cloth into the wet coat taking care to smooth out all wrinkles. Overlap all seams and joints by 50 mm. Apply a second coat of Idenden Sprayable Vapour Barrier Coating ET-150 AF after the first is touch dry and within 24 hours.  
  
B) ASBESTOS ENCAPSULATION  
Only sound asbestos should be coated, and surface preparation should be in line with local authority regulations. Apply Idenden PVA Sealer 30-17 as per the instructions on the Product Data Sheet. Using spray or brush, apply Idenden Sprayable Vapour Barrier Coating ET-150 AF to the entire surface ensuring any small crevices are properly coated. Apply a second coat of Idenden Sprayable Vapour Barrier Coating ET-150 AF the following day. Areas subject to mechanical damage such as joints may require additional protection with a reinforcement membrane.
3. COVERAGE  
Optimal performance is achieved by applying this minimum coverage rate:  
  
INTERNAL - Apply two coats, each at a rate of 2 square metres per litre to achieve a dry film thickness of 0.5 mm.

See final page for disclaimer.

Bostik Limited, Common Road, Stafford, ST16 3EH, England

Tel: +44 (0)1785 272727

Fax: +44 (0)1785 257898

www.bostik.co.uk

EXTERNAL - Apply two coats, the first at a rate of 1 square metres per litre and the second at a rate of 1.5 square metres per litre to achieve a dry film thickness of 0.8 mm.

#### 4. SPRAY INSTRUCTIONS

Idenden Sprayable Vapour Barrier Coating ET-150 AF may be sprayed with a variety of airless spray systems. However, the following system has proved successful:

Pump: Airlessco 5100 / Graco Ultra 1095  
Fluid Hose: 9mm diameter up to 15m hose length  
Gun: Airlessco 007  
Tip: 0.017-0.021 Reverse-a-quick nozzle

During spraying wear suitable respiratory equipment.

#### 5. DRYNESS TEST

A dried film can be tested by gently rubbing the coating with a clean damp rag. If no colour is removed, the film has dried effectively and will exhibit good water resistance. When used externally, adequate temporary protection/tenting should be provided as Idenden Sprayable Vapour Barrier Coating ET-150 AF dries. This will prevent damage from precipitation and aid good film formation and through drying.

#### 6. Clean application equipment and remove excess uncured coating with cold water and cured coating with white spirit.

Do not allow standing water to form on Idenden Sprayable Vapour Barrier Coating ET-150 AF coated surfaces by ensuring the upper surface is shaped to make a 15° slope prior to application of coating.

NOTE: Removal or encapsulation of asbestos containing material, dismantling of any confinement structure and disposal of both asbestos and contaminated materials should be done strictly within current regulations and codes of practice and only by an approved contractor.

#### Precautions in Use

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate health and safety data sheet for Idenden Sprayable Vapour Barrier Coating ET-150 AF.

---

#### Disclaimer - please read carefully

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Bostik Limited, Common Road, Stafford, ST16 3EH, England

Tel: +44 (0)1785 272727

Fax: +44 (0)1785 257898

www.bostik.co.uk